



Westlake Polymers

Enhancing your life every day

EB171

Medium Density Polyethylene

Application/Uses

- Beverage overwrap / shrink film
- Fresh produce bags
- Food packaging

Product Description

Westlake EB171 is a medium density polyethylene resin with high stiffness, good TD shrinkage and excellent toughness. It is suggested for uses in flexible packaging including shrink film and produce bags.

Typical Physical Properties^a

<u>Property</u>		<u>Test Method^b</u>	<u>Typical Value, Units^c</u>
Melt Index		D 1238	1.6 g/10 min
Density		D 1505	932 kg/m ³ (0.932 g/cm ³)
Haze		D 1003	8.0 %
Gloss @ 45°		D 2457	65
Ultimate Tensile	MD	D 882	3,800 psi
	TD	D 882	2,700 psi
Elongation	MD	D 882	300%
	TD	D 882	800%
1% Secant Modulus	MD	D 882	49,000 psi
	TD	D 882	65,000 psi
Dart Impact		D 1709	<65 g/mil

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.

NOTES

Test specimens for blown film: nominal thickness 1.3 mils; blow up ratio 2.5:1, die gap 50 mils.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Extrusion melt temperatures of 380° – 410° F are recommended for Westlake MDPE EB171 with blow-up ratios of 2.0:1 or higher to maximize TD shrinkage.

NOTICE

The data listed represents typical values as measured by Westlake. They are given for information only, and not guarantee of their accuracy is made. The product is sold upon condition that purchasers shall make their own tests to determine the characteristics of the product and the suitability of the product for their particular purpose.

Westlake makes no representation or warranty of any kind, express or implied, with respect to this product, whether as to merchantability, fitness for particular purpose or otherwise.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

WESTLAKE CHEMICAL CORPORATION

2801 Post Oak Blvd Suite 600 Houston, Texas
Customer Service: 1-800-545-9577